

IN THE CLAIMS:

Please cancel claims 11, 12, 30 and 43, without prejudice. This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS

1. (Currently Amended) A semiconductor substrate comprising:
a region of a-monocrystalline silicon-containing material having a
surface substantially free of oxidation;
a region of porous silicon; and
an organic layer immediately adjacent to the region of monocrystalline
silicon-containing material having more than half of its atoms being carbon and
hydrogen, wherein the organic layer is chemically bonded to the surface of the
silicon-containing material, wherein an electrical property selected from surface
recombination velocity, carrier lifetime, electronic efficiency, voltage, device
capacitance, contact resistance and resistance of a doped region of the
semiconductor substrate is improved as compared to the electrical property of the
substrate in the absence of the organic layer, and
wherein as a result of said organic layer being chemically bonded to
the surface of the silicon-containing material, said surface comprises a measurable
carrier lifetime for low-level injection of more than approximately 7.8 μs or for high-
level injection of more than approximately 12 μs , or a measurable surface
recombination velocity of less than approximately 1300 cm/s for low-level injection or
less than approximately 810 cm/s for high-level injection.

Claims 2-3. (Canceled)

4. (Previously Presented) The semiconductor substrate of claim 1, wherein the organic layer comprises a hydrocarbon.
5. (Previously Presented) The semiconductor substrate of claim 1, wherein the organic layer comprises a polymer.
6. (Withdrawn) The electrical structure of claim 1, wherein:
the silicon-containing material is at least part of a photovoltaic cell; and
the silicon-containing material comprises a region at the surface,
wherein the region has a dopant concentration of at least approximately $1E19$ atoms per cubic centimeter.
7. (Withdrawn) The electrical structure of claim 1, wherein:
the silicon-containing material is at least part of a channel region of a field-effect transistor; and
the organic layer is at least part of a gate dielectric for the field-effect transistor.
8. (Withdrawn) The electrical structure of claim 1, further comprising a high-k material wherein:
the silicon-containing material is at least part of a channel region of a field-effect transistor;

the organic layer lies between the silicon-containing material and the high-k material; and

the high-k material is at least part of a gate dielectric for the field-effect transistor.

Claims 9-12. (Canceled)

13. (Previously Presented) A process for forming a semiconductor substrate, comprising:

providing a monocrystalline silicon-containing material having a surface substantially free of oxidation; and

forming an organic layer having more than half of its atoms being carbon and hydrogen, wherein the organic layer is chemically bonded to the surface of the silicon-containing material, wherein an electrical property selected from surface recombination velocity, carrier lifetime, electronic efficiency, voltage, device capacitance, contact resistance, and resistance of a doped region of the semiconductor substrate is changed at compared to the electrical property of the substrate in the absence of the organic layer, thereby forming a semiconductor substrate, and

wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises a measurable carrier lifetime for low-level injection of more than approximately 7.8 μs or for high-level injection of more than approximately 12 μs , or a measurable surface

recombination velocity of less than approximately 1300 cm/s for low-level injection or 810 cm/s for high-level injection.

Claims 14-15. (Canceled)

16. (Original) The process of claim 13, wherein the organic layer comprises a monolayer.

17. (Original) The process of claim 13, wherein the organic layer comprises a polymer.

18. (Withdrawn) The process of claim 13, further comprising doping a portion of the silicon-containing material at the surface, wherein:

the portion has a dopant concentration of at least approximately 1×10^{19} atoms per cubic centimeter immediately adjacent to the surface;

the silicon-containing material is at least part of a photovoltaic cell; and
doping is performed before forming the organic layer.

19. (Withdrawn) The process of claim 13, further comprising forming a gate electrode over the organic layer, wherein:

the silicon-containing material is at least part of a channel region of a field-effect transistor;

the organic layer is at least part of a gate dielectric for the field-effect transistor; and

the gate electrode is a control electrode for the field-effect transistor.

20. (Withdrawn) The process of claim 13, further comprising:

forming a high-k material; and

forming a gate electrode, wherein:

the silicon-containing material is at least part of a channel region of a field-effect transistor;

the organic layer lies between the silicon-containing material and the high-k material; and

the high-k material is at least part of a gate dielectric for the field-effect transistor and lies between the silicon-containing material and the gate electrode.

21. (Original) The process of claim 13, wherein forming the organic layer comprises:

activating the surface of the silicon-containing material to form an activated surface;

reacting the activated surface with a chemical, wherein during the reaction, a hydrocarbon group becomes chemically bonded to the silicon-containing material.

22. (Original) The process of claim 21, wherein activating comprises halogenating the surface of the silicon-containing material to form the activated surface.

23. (Original) The process of claim 22, wherein the hydrocarbon group has no more than nine carbon atoms.

24. (Original) The process of claim 23, wherein the hydrocarbon group is an alkyl group.

25. (Original) The process of claim 21, wherein the hydrocarbon group is an allyl group.

26. (Currently Amended) The process of claim ~~24~~ 25, further comprising forming a polymer layer from the allyl group.

27. (Original) The process of claim 21, wherein the hydrocarbon group is an alkoxide group.

Claims 28-30. (Canceled)

31. (Withdrawn) A process for forming an electrical device comprising:
forming a patterned insulating layer over at least of the electrical device,
wherein:

the patterned insulating layer defines an opening;

a silicon-containing region has an exposed portion at the opening; and

the silicon-containing region is at least part of an electrical component within the electrical device;

forming an organic layer chemically bonded to the surface of the silicon-containing region;

removing the organic layer; and

forming a metal-containing layer after removing the organic layer, wherein at least a portion of the metal-containing layer contacts the exposed portion of the silicon-containing region, and wherein the metal-containing layer is part of an electrical connection to the silicon-containing region.

32. (Withdrawn) The process of claim 31, further comprising allowing at least approximately four hours to elapse between forming the organic layer and removing the organic layer.

33. (Withdrawn) The process of claim 31, further comprising annealing the non-insulating layer to form a metal silicide from the metal-containing layer and the silicon-containing region.

34. (Withdrawn) The process of claim 31, wherein no etching act is performed between forming and removing the organic layer.

35. (Withdrawn) A process for forming an electrical device comprising:
forming a patterned insulating layer over at least of the electrical device,
wherein:

the patterned insulating layer defines an opening;

a silicon-containing region has an exposed portion at the opening; and

the silicon-containing region is at least part of an electrical component within the electrical device;

forming an organic layer chemically bonded to the surface of the crystalline material;

removing the organic layer; and

forming a dopant-source layer that contacts the exposed portion of the silicon-containing region.

36. (Withdrawn) The process of claim 35, further comprising allowing at least approximately four hours to elapse between forming the organic layer and removing the organic layer.

37. (Withdrawn) The process of claim 35, wherein the dopant-source layer comprises at least approximately 90 percent of at least one Group IVA element.

38. (Withdrawn) The process of claim 35, further comprising annealing the dopant-source layer to diffuse at least a portion of the dopant atoms into the silicon-containing region.

39. (Withdrawn) The process of claim 35, wherein no etching act is performed between forming and removing the organic layer.

40. (Withdrawn) An electrical structure comprising:

a silicon-containing material having a surface and at least one electrode, wherein the silicon-containing material is capable of conducting electric current, and an organic layer chemically bonded to the surface of the silicon-containing material, wherein an electrical property of the electrical structure is significantly improved compared to a same structure without the organic layer.

41. (Currently Amended) The ~~semiconductor substrate~~ process of claim 1 ~~13~~, wherein ~~the structure without the organic layer comprises a silicon-containing material having a surface, wherein the~~ monocrystalline silicon-containing material surface is a hydrogen terminated surface.

42-43. (Canceled)

44. (Previously Presented) The silicon substrate of claim 1, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises a methylated surface with measurable carrier lifetimes for low-level injection of at least approximately 260 μ s or for high-level injection of at least approximately 290 μ s, or with measurable surface recombination velocities of not more than approximately 17 cm/s for low-level injection or 21 cm/s for high-level injection, or combinations thereof.

45. (Previously Presented) The silicon substrate of claim 1, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises an ethylated surface with measurable

carrier lifetimes of more than approximately 40 μ s, or with measurable surface recombination velocities of less than approximately 350 cm/s, or both.

46. (Previously Presented) The silicon substrate of claim 1, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises an ethylated surface with measurable carrier lifetimes of more than approximately 30 μ s, or with measurable surface recombination velocities of less than approximately 470 cm/s, or both.

47. (Previously Presented) The silicon substrate of claim 1, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises a hexylated, octylated or dodecylated surface with measurable carrier lifetimes of at least approximately 20 μ s, or with measurable surface recombination velocities of not more than approximately 200 cm/s, or both.

48. (Previously Presented) The silicon substrate of claim 1, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises an alkoxylated surface with measurable carrier lifetimes of more than approximately 150 μ s for low-level injection or more than approximately 140 μ s for high-level injection, or with measurable surface recombination velocities of not more than approximately 70 cm/s, or combinations thereof.

49. (Previously Presented) The process of claim 13, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises a methylated surface with measurable carrier lifetimes for low-level injection of at least approximately 260 μ s or for high-level injection of at least approximately 290 μ s, or with measurable surface recombination velocities of not more than approximately 17 cm/s for low-level injection or 21 cm/s for high-level injection, or combinations thereof.

50. (Previously Presented) The process of claim 13, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises an ethylated surface with measurable carrier lifetimes of more than approximately 40 μ s or with measurable surface recombination velocities of less than approximately 350 cm/s, or both.

51. (Previously Presented) The process of claim 13, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises an ethylated surface with measurable carrier lifetimes of more than approximately 30 μ s, or with measurable surface recombination velocities of less than approximately 470 cm/s, or both.

52. (Previously Presented) The process of claim 13, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises a hexylated, octylated or dodecylated surface with

measurable carrier lifetimes of at least approximately 20 μ s, or with measurable surface recombination velocities of not more than approximately 200 cm/s, or both.

53. (Previously Presented) The process of claim 13, wherein as a result of said organic layer being chemically bonded to the surface of the silicon-containing material, said surface comprises an alkoxylated surface with measurable carrier lifetimes of more than approximately 150 μ s for low-level injection or more than approximately 140 μ s for high-level injection, or with measurable surface recombination velocities of not more than approximately 70 cm/s, or combinations thereof.